

RES-30 30/20 NİKEL KROM YUVARLAK TEL

°C	100	200	300	400	500	600	700	800	900	1100	1200
Ct	1,03	1,07	1,1	1,13	1,15	1,18	1,19	1,21	1,23	1,25	
Çap	mm ²		ohm/mt (20°C)		Gr/mt						
6,000	28,26000		0,0368		223,4000						
5,000	19,62500		0,0530		155,1000						
4,500	15,89630		0,0654		125,6000						
4,000	12,56000		0,0828		99,3000						
3,500	9,61630		0,1081		75,9900						
3,250	8,29160		0,1254		65,5300						
3,000	7,06500		0,1471		55,9300						
2,800	6,15440		0,1689		48,6400						
2,500	4,90630		0,2119		38,7700						
2,250	3,97410		0,2616		31,4100						
2,000	3,14000		0,3310		24,8200						
1,900	2,83390		0,3668		22,4000						
1,800	2,54340		0,4087		20,1000						
1,700	2,26870		0,4582		17,9300						
1,600	2,00960		0,5173		15,8800						
1,500	1,76630		0,5885		13,9600						
1,400	1,53860		0,6756		12,1600						
1,300	1,32670		0,7835		10,4900						
1,200	1,13040		0,9039		8,9990						
1,100	0,94990		1,0444		7,5080						
1,000	0,78500		1,2242		6,2030						
0,950	0,70850		1,4672		5,5990						
0,900	0,63590		1,6348		5,0250						
0,850	0,56720		1,8328		4,4820						
0,800	0,50240		2,0690		3,9710						
0,750	0,44160		2,3541		3,4900						
0,700	0,38470		2,7024		3,0400						
0,650	0,33170		3,1341		2,6210						
0,600	0,28260		3,6782		2,2340						
0,550	0,23750		4,3774		1,8770						
0,500	0,19630		5,2967		1,5510						
0,475	0,18090		5,8689		1,4000						
0,450	0,15900		6,5391		1,2560						
0,425	0,13850		7,3310		1,1210						
0,400	0,12560		8,2761		0,9930						
0,375	0,11340		9,4163		0,8726						
0,350	0,09620		10,8100		0,7599						
0,320	0,08040		12,9310		0,6353						
0,300	0,07070		14,7130		0,5583						
0,280	0,06150		16,8900		0,4864						
0,250	0,04910		21,1870		0,3877						
0,240	0,04520		22,9890		0,3574						
0,220	0,03800		27,3590		0,3003						
0,200	0,03140		33,1040		0,2482						
0,190	0,02840		36,6810		0,2240						
0,180	0,02540		40,8690		0,2010						
0,170	0,02270		45,8190		0,1793						
0,160	0,02010		51,7250		0,1588						
0,150	0,01770		58,8520		0,1396						
0,140	0,01540		67,5600		0,1216						
0,130	0,01330		78,3530		0,1049						
0,120	0,01130		91,9560		0,0893						
0,110	0,00950		109,4400		0,7510						
0,100	0,00790		132,4200		0,0620						
0,090	0,00636		163,5600		0,0503						
0,080	0,00503		207,0100		0,0397						
0,070	0,00385		270,3800		0,03030						
0,060	0,00283		368,0100		0,0224						
0,050	0,00196		529,9400		0,0155						
0,040	0,00126		828,0300		0,0099						
0,030	0,00071		1472,0500		0,0056						

çalışma sıcaklığındaki direnci bulmak için "Ct" katsayısı ile 20°C deki ohm direncini çarpınız